

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in this application.

Listing of Claims:

1. (Currently Amended) A film comprising an A/B/A structure, wherein the A layers are skin layers, which may be the same or different, each independently comprising an mLLDPE having a density of between about 0.918 and 0.927 g/cm³, and the B layer is a core layer comprising a blend comprising an HDPE and an LDPE.
2. (Cancelled).
3. (Original) The film according to Claim 1, wherein at least one of said A layers further comprises an HDPE.
4. (Currently Amended) The film according to ~~Claim 3~~ Claim 1, wherein at least one of said A layers further comprises an HDPE having said HDPE has a density of between about 0.940 and 0.970 g/cm³.
5. (Currently amended) The film according to ~~Claim 4~~ Claim 1, wherein at least one of said A layers further comprises an HDPE having said HDPE has a density of between about 0.960 to about 0.965 g/cm³.
6. (Original) The film according to Claim 1, wherein the HDPE in said B layer has a density of between about 0.940 and 0.970 g/cm³.
7. (Currently Amended) The film according to Claim 6, wherein said HDPE in said B layer has a density of between about 0.960 to about 0.965 g/cm³.
8. (Original) The film according to Claim 1, wherein said LDPE has a density of between about 0.916 to 0.935 g/cm³.
9. (Original) The film according to Claim 1, wherein said LDPE has a density of between about 0.925 to 0.930 g/cm³.
10. (Currently Amended) The multilayer film structure according to Claim 1, wherein said core layer B comprises 60-90 wt.% LDPE, and 40-10 wt.% HDPE, and said skin layers A are each independently selected from a blend comprising 80-100 wt.% mPE, and 20-0 wt.% HDPE.

11. (Currently amended) The multilayer film structure according to ~~Claim 10~~ Claim 1, wherein said core layer B comprises 70-80 wt.% LDPE, 30-20 wt.% HDPE, and said skin layers A are each independently selected from a blend comprising 85-95 wt.% mPE, and 15-5 wt.% HDPE.
12. (Original) The multilayer film structure according to Claim 10, wherein said layers A and layer B, when formed into a coextruded structure A/B/A having a total thickness of less than 50 microns, has a 1% secant Modulus MD of at least 400 MPa, and a 1% secant Modulus TD of at least 400 MPa, both measured in accordance with ASTM D882.
13. (Original) The multilayer film structure according to Claim 12, having a 1 % secant Modulus MD of at least 500 MPa, and a 1% secant Modulus TD of at least 500 MPa, measured in accordance with ASTM D882.
14. (Original) The multilayer film structure according to Claim 12, having a 1% secant Modulus TD of 600 MPa, measured in accordance with ASTM D882.
15. (Original) The multilayer film structure according to Claims 10, wherein said layers A and layer B, when formed into a coextruded structure A/B/A having a total thickness of less than 50 microns, has a difference in Gloss 20° and 60° of 2% or less, the Gloss values measured in accordance with ASTM D2457.
16. (Original) The multilayer film structure according to Claim 1, further comprising at least one layer between at least one of said A/B layers, said at least one layer selected from the group consisting of a tie layer, a reprocessed material layer, and a layer selected from blends comprising an HDPE and an LDPE.
17. (Original) A coextruded, heat shrinkable film according to Claim 1.
18. (Original) A collation shrink-wrapped structure comprising a group of items wrapped by means of a film according to Claim 16.
19. (New) A three layer film, comprising:
 - a first skin layer;
 - a core layer; and
 - a second skin layer,

wherein the first and second skin layers are the same or different, each independently comprising an mLLDPE having a density of between about 0.918 and 0.927 g/cm³, and wherein the core layer comprises an HDPE and LDPE blend.

20. (New) The film according to Claim 19, wherein the first skin layers or the second skin layer or both skin layers further comprise HDPE.